

Polyprop Greyback Roll-Up Film 200mic

200mic matte finish PP banner
PVC Free
Grey back for light block-out
Excellent tear and scratch resistance
Designed for use with roller banners and POS applications
100% PP Film, recyclable

Suitable for use with:



Order Code	W (mm)	L (mm)	Weight (ums)
ISB275588	914	50	200



Polyprop Greyback Roll-Up Film 200mic

Specification	Test Method	Unit	Result	
Total Thickness	GB/T 451.3-2002	um	210±5	
Total Weight	GB/T 6544-2008	gsm	165±5	
Opacity Ratio	GB/T 1573-1988	%	≥ 95	
Whiteness	GB/T 8940.1-1988	%	95±5	
Glossy	GB/T 9754-2007	Gs	6.0±1.0	
Tensile Strength	TD	GB/T12914-1991	Mpa	≥ 110
	MD			≥ 50
Stiffness	TD	GB/ 22364-2008	mN.m	3.3±0.5
	MD			2.5±0.5

NOTE: Information listed above is based on our general experience and observation and is given in good faith and does not constitute terms or part of any contract. We will not accept responsibilities with respects to factors outside our knowledge, including direct, indirect or consequential loss. Values without tolerance statements are values with a tolerance of ±5%. Media will often have a natural base, therefore there can be variances from batch to batch. Shelf life is 2 years, storage temperature 15-25 °C, RH 40-60%. Repack opened rolls when not in use. Allow material to adapt to room conditions for 24 hours prior to printing. We always recommend a test print and the customer is deemed to have ensured suitability of the material for the application intended and assumes all associated risks and liabilities in connection with specifying, using or not being able to use any product. Always hem edges when used in hanging or suspended applications by high-tack banner tape or welding. Grommets or eyelets should always be inserted in double-hemmed edges, four layers at corners. Remember that sewing in some applications can affect the integrity of the media. Technical specifications may change without notice. E & OE.