

Polyprop Greyback Roll-Up Film 230mic

260mic matte finish PP banner
Grey back for block-out
Excellent tear and scratch resistant
Poly resin coating for Eco-Sol, UV
Ideal for outdoor banners application

Suitable for use with:



Order Code	W (mm)	L (mm)	Weight (ums)
ISB275451	914	30	230



Polyprop Greyback Roll-Up Film 230mic

DESCRIPTION	RESULT
BASE MATERIALS	260usm grey back white PP
COATING TYPE	Poly resin C1S
RELEASE PAPER	-
GLUE TYPE	-
FINISH	MATTE (4.5@60°)
LAB	97, +2, -4.5
OPACITY	100%
SHELF TIME	24 MONTHS
APPLICATION TEMPERATURE	-20°C- 65°C (-4F - 150F)
DURABILITY	UP TO 12Months

NOTE: Information listed above is based on our general experience and observation and is given in good faith and does not constitute terms or part of any contract. We will not accept responsibilities with respects to factors outside our knowledge, including direct, indirect or consequential loss. Values without tolerance statements are values with a tolerance of $\pm 5\%$. Media will often have a natural base, therefore there can be variances from batch to batch. Shelf life is 2 years, storage temperature 15-25 °C, RH 40-60%. Repack opened rolls when not in use. Allow material to adapt to room conditions for 24 hours prior to printing. We always recommend a test print and the customer is deemed to have ensured suitability of the material for the application intended and assumes all associated risks and liabilities in connection with specifying, using or not being able to use any product. Always hem edges when used in hanging or suspended applications by high-tack banner tape or welding. Grommets or eyelets should always be inserted in double-hemmed edges, four layers at corners. Remember that sewing in some applications can affect the integrity of the media. Technical specifications may change without notice. E & OE.