

Max-Flat Backlit Media 480

Backlit display media with consistent light diffusion and excellent lay-flat properties.

FEATURES AND BENEFITS

- Superb, stable lay-flat properties
- No lamination required
- Suitable for indoor use
- Premium grade product
- Available in 3.2m widths

Suitable for use with:



Order Code	W (mm)	L (mm)	Weight (gm \boxtimes)
ISB274660	2200	50	480
ISB274663	3200	50	480

Max-Flat Backlit Media 480

TECHNICAL SPECIFICATIONS

Properties	Test Method	Result	Unit
Total weight	DIN53352 BS3424 Method5A	420	g/sq.m
Tensile Strength (W/F)	DIN53354 BS3424 Method6A	1182/1173	N/5cm
Tear Resistance (W/F)	DIN53356 BS3424 Method7A	34/27	N/5cm
Temperature Resistance	DIN53357 BS3425 Method10	-20 - +70	°C
Max Width		3.2	Meter
Flammability	B1, B2, M2, NFPA701, etc.	On Application	

NOTE: Information listed above is based on our general experience and observation and is given in good faith and does not constitute terms or part of any contract. We will not accept responsibilities with respects to factors outside our knowledge, including direct, indirect or consequential loss. Values without tolerance statements are values with a tolerance of $\pm 5\%$. Media will often have a natural base, therefore there can be variances from batch to batch. Shelf life is 2 years, storage temperature 15-25 °C, RH 40-60%. Repack opened rolls when not in use. Allow material to adapt to room conditions for 24 hours prior to printing. We always recommend a test print and the customer is deemed to have ensured suitability of the material for the application intended and assumes all associated risks and liabilities in connection with specifying, using or not being able to use any product. Always hem edges when used in hanging or suspended applications by high-tack banner tape or welding. Grommets or eyelets should always be inserted in double-hemmed edges, four layers at corners. Remember that sewing in some applications can affect the integrity of the media. Technical specifications may change without notice. E & OE.