

# TECHNICAL SPECIFICATIONS

## ENVIROTECH® PP260 PVC FREE FLEX BANNER 260G/M2

### Features & Benefits

- Lightweight yet hardwearing 100% PVC free banner
- Superior strength and smoothness, looks like PVC
- PP based allows for closed-loop recycling
- Self cleaning and weather resistant properties
- Applications: Outdoor banners, exhibition graphics

### Printing & Finishing

- The material should reach room temperature and a relative humidity of approx. 50% prior to printing.
- Ensure the material is kept free of dust, dirt and static. We recommend using gloves when handling the material.
- Conduct a print test prior to printing the material for a live project.
- 3.2m rolls and above are wound Print Side In (PSI).
- Suitable for printing with UV-C and Latex printers.

- For maximum scratch resistance, we recommend leaving the prints for a full 24hrs after printing.
- Can be hemmed and well suited to hot wedge or hot air welding

### Storage

- We recommend storing the material in its original tube and wrapping when not in use.
- Material can be stored for up to 2 years when stored in the original packaging
- Store between 20°C and 25°C at 50% relative humidity

### Laminating

- This material does not require lamination. However, should the user decide to apply liquid laminate, it is their responsibility to test.



Characteristic	Result
Finished Weight	260 g/m2
Peel Strength	40 N/5cm
Tensile Strength (Warp)	900 N/5cm
Tensile Strength (Weft)	890 N/5cm
Tear Strength (Warp)	410 N/5cm
Tear Strength (Weft)	375 N/5cm

Product Code	Width (mm)	Length (m)
ISB276411	1100	50
ISB276414	1370	50
ISB276417	1600	50
ISB276420	2500	50
ISB276371	3200	50
ISB276374	3200	100

We operate a policy of continuous improvement and we reserve the right to alter products and specifications to reflect this without prior notice. Any information given either verbally or in writing is approximate only and given in good faith and does not constitute terms or part of any contract. We do not accept liability for variance including direct, indirect or consequential loss. The customer is deemed to have determined the suitability of the product for the use intended and assumes all associated risks and liabilities in connection with specifying, using or being unable to use any of the products.