

## Kinetix Ferrous Sheet Textile

This ferrous sheet textile is not magnetic, however is used to attach magnets to it. Ideal for creating graphics that can be applied to a self adhesive magnetic wall.

### FEATURES AND BENEFITS

- Ideal surface for attaching magnets to
- Constructed of anti-rust steel coating, white canvas and a top coating.

Suitable for use with:



Order Code	W (mm)	L (mm)	Weight (g/m2)
INM100214	1270	30	470

# Kinetix Ferrous Sheet Textile

## TECHNICAL SPECIFICATIONS

Properties	Result	Unit
Thickness	0.38	mm
Weight	470	g/m <sup>2</sup>
Whiteness	75-80	Wb
Brightness	2-5	Gs
Tensile Strength (Vertical)	25-35	MPa
Tensile Strength (Parallel)	80-100	MPa
Breaking Elongation Ratio (Vertical)	10~20	%
Breaking Elongation Ratio (Parallel)	10~20	%
Lifting weight	3.5	g/cm <sup>2</sup>

*NOTE: Information listed above is based on our general experience and observation and is given in good faith and does not constitute terms or part of any contract. We will not accept responsibilities with respects to factors outside our knowledge, including direct, indirect or consequential loss. Values without tolerance statements are values with a tolerance of ±5%. Media will often have a natural base, therefore there can be variances from batch to batch. Shelf life is 2 years, storage temperature 15-25 °C, RH 40-60%. Repack opened rolls when not in use. Allow material to adapt to room conditions for 24 hours prior to printing. We always recommend a test print and the customer is deemed to have ensured suitability of the material for the application intended and assumes all associated risks and liabilities in connection with specifying, using or not being able to use any product. Always hem edges when used in hanging or suspended applications by high-tack banner tape or welding. Grommets or eyelets should always be inserted in double-hemmed edges, four layers at corners. Remember that sewing in some applications can affect the integrity of the media. Technical specifications may change without notice. E & OE.*