

## Monomeric Permanent Clear Vinyl / Laminate 80mic Gloss & Matt

A clear 80mic monomeric vinyl with a permanent adhesive, designed for use as a clear vinyl or lamination film.

Available in Gloss and Matt finishes it is designed to be applied to flat or slightly curved surfaces.

Suitable for use with:



Order Code	Finish	W (mm)	L (mm)	Thickness (ums)
INV214126	Gloss	1370	50	80
INV214165	Gloss	1600	50	80
INV214132	Matt	1370	50	80
INV214168	Matt	1600	50	80

## Monomeric Permanent Clear Vinyl / Laminate 80mic Gloss & Matt

### Technical Data

Property	Result
Colour	Clear
Film	Monomeric Calendared Vinyl
Gloss	Gloss & Matt
Thickness (Face Film)	80mic $\pm$ 10mic
Adhesive Type	Permanent, acrylic pressure sensitive adhesive
Adhesive Colour	Clear
Coating Weight (Dry)	20g/m <sup>2</sup> $\pm$ 2g/m <sup>2</sup>
Liner	One side PE coated white wood-pulp paper
Weight (Liner)	120g/m <sup>2</sup> $\pm$ 5g/m <sup>2</sup>
Application Surfaces	Flat and simple curved surfaces
Application Substrates	Metal, Paint, Rigid Plastic
Application Temperature Range	3 ~ 38°C
Removability	N/A

*NOTE: Information listed above is based on our general experience and observation and is given in good faith and does not constitute terms or part of any contract. We will not accept responsibilities with respects to factors outside our knowledge, including direct, indirect or consequential loss. Values without tolerance statements are values with a tolerance of  $\pm$ 5%. Media will often have a natural base, therefore there can be variances from batch to batch. Shelf life is 2 years, storage temperature 15-25 °C, RH 40-60%. Repack opened rolls when not in use. Allow material to adapt to room conditions for 24 hours prior to printing. We always recommend a test print and the customer is deemed to have ensured suitability of the material for the application intended and assumes all associated risks and liabilities in connection with specifying, using or not being able to use any product. Always hem edges when used in hanging or suspended applications by high-tack banner tape or welding. Grommets or eyelets should always be inserted in double-hemmed edges, four layers at corners. Remember that sewing in some applications can affect the integrity of the media. Technical specifications may change without notice. E & OE.*