

Seemee



Seemee Tarpaulin

| | Supreme | Extra |
|--|--|--------------------------------------|
| | Technical properties | |
| Product reference | B2011 | B2033 |
| Application | printable truck cover | printable truck cover |
| Printing technology | solvent, UV, latex | solvent, UV, latex |
| Support cloth DIN ISO 2076 | PES | PES |
| Type of coating | PVC | PVC |
| Weight DIN EN ISO 2286-2 | 670 g/m² - 19,8 oz/sq.yd | 900 g/m² - 26,5 oz/sq.yd |
| Width DIN EN ISO 2286-1 | 320 cm - 126 in. | 300 cm - 118 in. |
| | Roll length | |
| For all widths | 50 lm • 54.68 yd | 50 lm • 54.68 yd |
| | Physical properties | |
| Tensile strength (warp/weft) DIN EN ISO 1421 | 300/300 daN/5 cm 674/674 lbs/2 in | 400/380 daN/5 cm 899/854 lbs/2 in |
| Tear strength (warp/weft) DIN 53363 | 30/30 daN 67/67 lbs | 45/40 daN 101/90 lbs |
| | Fire resistance | |
| Rating | - | ISO 3795 < 100 mm/min |
| | Management system | |
| | Quality: ISO 9001 • Environment: ISO 14001 • | F |





¹ Summarizes the group's CSR project focused on human, to align economic performance and positive impact.

The technical data above are averaged values with a +/-5% tolerance.

The purchaser of our products is responsible for their application or transformation in relation to possible third party rights. The purchaser of our products is responsible for their installation in compliance with the standards, working practices and safety regulations of their destination country. Please refer to our warranty document with regard to contractual liability.

Values quoted in this document are commonly used test results for design purposes. They are given for information only in order to offer our customers optimum usage of our products. Our products are subject to improvements resulting from technical developments and we reserve the right to modify their characteristics at any time. The purchaser of our products is responsible for checking the above data.

The colours and textures presented are included for information only.

