

# TECHNICAL SPECIFICATIONS

## VISTAMAX® SC150C CLEAR STATIC CLING 150MIC

### Features & Benefits

- High transparency
- One year durability of static adhesion on smooth and clean application surface
- Easy installation, repositioning and removal on glass and other smooth surfaces.

### Printing

- The material should reach room temperature and a relative humidity of approx. 50% prior to printing.
- Ensure the material is kept free of dust, dirt and static. We recommend using gloves when handling the material.
- Conduct a print test prior to printing the material for a live project.
- Rolls are wound Print Side Out (PSO).

### Application

- Suitable for application to flat or slightly curved surfaces
- This product should be applied to high energy surfaces like glass or smooth metal.
- It is the responsibility of the user to determine the suitability of the material for the application.
- Test the application with a small piece of the material prior to doing the full application

### Storage

- We recommend storing the material in its original tube and wrapping when not in use.
- Material can be stored for up to 12 months when stored in the original packaging
- Store between 10°C and 35°C at 50% relative humidity



Characteristic	Result
Film	Transparent Static PVC
Liner	PEK Paper Liner
Thickness (Film)	150mic
Thickness (Liner)	180mic
Total Thickness	330mic
Weight (Film)	192g/m <sup>2</sup>
Weight (Liner)	170g/m <sup>2</sup>
Total Weight	362g/m <sup>2</sup>
Storage Temperature	10-35°C
Storage Humidity	50%
Lifespan	12months

Product Code	Width (mm)	Length (m)
INV214471	1040	100
INV214474	1220	100
INV214477	1370	50
INV214480	1400	100

We operate a policy of continuous improvement and we reserve the right to alter products and specifications to reflect this without prior notice. Any information given either verbally or in writing is approximate only and given in good faith and does not constitute terms or part of any contract. We do not accept liability for variance including direct, indirect or consequential loss. The customer is deemed to have determined the suitability of the product for the use intended and assumes all associated risks and liabilities in connection with specifying, using or being unable to use any of the products.